

















2mm



2.5mm

Altro Transflor Momentum™

Colours Colores Farben	12		
Flooring Type Tipo de pavimento Belagsart		EN13845	Safety flooring Suelo de seguridad antideslizante Sicherheitsbodenbelag
Slip Resistance Resistencia al deslizamiento Rutschsicherheit		TRRL DIN 51130 EN13845 ASTM D2047	≥ 40 R10 ESf ≥ 0.6
Thickness Espesor Total Gesamtdicke		EN 428	2mm / 0.08" 2.5mm / 0.10"
Wear Layer Capa de uso Nutzschicht		EN 429	1.0mm 0.04"
Flexibility Flexibilidad Flexibilität		EN 435	Pass Conforme geeignet
Weight Peso Flächengewicht		EN 430	2.5kg / m ² or 4.60lb / yd ² 3.0kg / m ² or 5.53lb / yd ²
Roll Dimensions Dimensiones del rollo Rollenabmessungen		EN 426	2m x 20m - 40m ² 66'x6.58'
Light Fastness Resistencia a la luz Lichtechtheit		EN 20105-B02	≥6
Wear Resistance Abrasión Verschleißverhalten		EN13845 Annex D	≤10% Particles lost over 50,000 cycles ≤10% de las partículas perdidas en 50,000 ciclos ≤10% Partikelverlust bei 50.000 Umdrehungen
Indentation Punzonamiento Resteindruck		EN 433	≤ 0.1mm ≤ 0.004"
Fire Performance Reacción al fuego Brandverhalten		EN ISO 9239-1 DIN 5510 ASTM E648 ASTM E662 BS 6853	≥8kW/m ² SF3 FED ≤1 Class 1 / Clase 1 / Klasse 1 Ds @ 1.5min ≤100 Ds @ 4min ≤200 Category Ia
Chemical Resistance Resistencia a los productos químicos Chemikalieneinwirkung		EN 425	Good Buena beständig
Castor Chair Abrasion Huellas de sillas de ruedas Stuhlrollenbeanspruchung		EN 425	Pass Conforme geeignet
Dimensional Stability Estabilidad dimensional Formstabilität		EN 434	≤0.4%

All information is correct at the time of print and is subject to change without prior notice. Visit us online for more information and updates. This product has never contained phthalate plasticisers.