



Altro Transflor Wood™ Patent No. (专利号) GB 2 462 167

Flooring type 地板类型		EN 13845 ASTM F1303	Safety flooring 安全地板
Thickness 厚度		EN ISO 24346	2.2 mm / 0.088"
Wear layer 耐磨层		EN ISO 24340	0.7 mm / 0.027"
Roll dimensions 成卷尺寸		EN ISO 24341	2m x 20m = 40m ² 6'7" x 65'7"
Weight 重量		EN ISO 23977	2.68 kg/m ² 4.93 lb/sy
Fire Performance 防火		ECE R-118 FMVSS 302 / CMVSS 302	Pass / 通过 Pass / 通过
Slip resistance 防滑		BAM EN 13893 EN 13845 ASTM D2047 PTV DIN 51130	Dry - very slip resistant 干 - 非常防滑 Wet - slip resistant 湿 - 防滑 DS ESf ≥0.6 ≥ 36 R10
Flexibility 弯曲性		EN 435 ASTM F1303	Pass 通过
Light fastness 色牢度		EN ISO 105-B02	≥6
Wear resistance 耐磨性		EN13845	≤10% particles lost over 50000 cycles ≤10% 颗粒损失 50000转
Castor Chair Abrasion 椅子脚轮试验		EN 425	Pass 通过
Indentation 残余凹陷		EN ISO 24343-1 ASTM F970	≤ 0.10 mm
Chemical resistance 耐污染性		EN 423	Good 好
Electrical behaviours 导电性		EN 1815	≤ 2kV Antistatic ≤ 2kV 抗静电
VOC emissions VOC排放		IAC Gold	Pass 通过

All information is correct at the time of print and is subject to change without prior notice. Visit us online for more information and updates. This product has never contained phthalate plasticisers. 所有信息在印刷时都经过校对，如有更改，恕不另行通知。在线访问我们获取更多信息和更新。该产品从未使用过邻苯类增塑剂。 www.altro.com, www.altro.net.cn